

GEOMEMBRANE LINER
ENGINEERING SPECIFICATION GUIDE



POLYVINYL CHLORIDE (PVC)

PROPERTIES	TEST METHOD	SPECIFIED VALUES				
Thickness	ASTM D 5199	20 ± 1 mil 0.51 ± 0.03 mm	30 ± 1.5 mil .76 ± .04 mm	40 ± 2 mil 1.02 ± .05 mm	50 ± 2.5 mil 1.27 ± .06 mm	60 ± 3 mils 1.52 ± .08 mm
Tensile Properties	ASTM D 882 Min					
Strength at Break		48 lbs/in 8.4 kN/m	73 lbs/in 12.8 kN/m	97 lbs/in 17.0 kN/m	116 lbs/in 20.3 kN/m	137 lbs/in 24.0 kN/m
Elongation		360%	380%	430%	430%	450%
Modulus @ 100%		21 lbs/in 3.7 kN/m	32 lbs/in 5.6 kN/m	40 lbs/in 7.0 kN/m	50 lbs/in 8.8 kN/m	60 lbs/in 10.5 kN/m
Tear Strength	ASTM D 1004 Min.	6 lbs 27 N	8 lbs 35 N	10 lbs 44 N	13 lbs 58 N	15 lbs 67 N
Dimensional Stability	ASTM D 1204 Max Chg	4%	3%	3%	3%	3%
Low Temperature Impact	ASTM D 1790 Pass	-15°F -26°C	-20°F -29 °C	-20°F -29°C	-20°F -29°C	-20°F -29°C
Index Properties						
Specific Gravity	ASTM D 792 Typical	1.2 g/cc	1.2 g/cc	1.2 g/cc	1.2 g/cc	1.2 g/cc
Water Extraction % loss (max.)	ASTM D 1239 Max Loss	0.15%	0.15%	0.20%	0.20%	0.20%
Average Plasticizer Molecular Weight	ASTM D 2124	400	400	400	400	400
Volatility Loss	ASTM D 1203 Max Loss	0.9%	0.7%	0.5%	0.5%	0.5%
Soil Burial						
Break Strength	G160 Max Chg	5%	5%	5%	5%	5%
Elongation		20%	20%	20%	20%	20%
Modulus at 100%		20%	20%	20%	20%	20%
Hydrostatic Resistance	ASTM D 751 Min.	68 psi 470 kPa	100 psi 690 kPa	120 psi 830 kPa	150 psi 1030 kPa	180 psi 1240 kPa
Seam Strengths						
Shear Strength	ASTM D 882 Min	38.4 lbs/in 6.7 kN/m	58.4 lbs/in 10 kN/m	77.6 lbs/in 14 kN/m	96 lbs/in 17 kN/m	116 lbs/in 20 kN/m
Peel Strength	ASTM D-882 Min	12.5 lbs/in 2.2 kN/m	15 lbs/in 2.6 kN/m	15 lbs/in 2.6 kN/m	15 lbs/in 2.6 kN/m	15 lbs/in 2.6 kN/m

The information contained herein is offered free of charge, and is, to our best knowledge, true and accurate; however, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. There is no expressed warranty and no implied warranty of merchantability or of fitness for purpose of the product or products described herein. In submitting this information, no liability is assumed or license or other rights implied given with respect to any existing or pending patent, patent applications or trademarks. The observance of all legal regulations and patents is the responsibility of the user.

www.watersaver.com

PO Box 16465 Denver, CO 80216 303-289-1818 FAX 303-287-3136

Equal Opportunity Employer