



Established 1953

WATERSAVER COMPANY, INC.

P.O. BOX 16465 DENVER, COLORADO 80216-0465

www.watersaver.com

Phone: 303-289-1818

1-800-525-2424

Fax: 303-287-3136

Plant and Office • 5870 E. 56th Avenue, Commerce City, Colorado 80022-3932

CFS5027 Silt Fence Fabric

Property	Test Method	Unit	Roll Value
Grab Tensile	ASTM D 4632	Lbs	149 X 158
Grab Elongation	ASTM D 4632	%	17.3/17.4
Mullen Burst	ASTM D 3786	PSI	250
Puncture	ASTM D 4833	Lbs	60
Trapezoidal Tear	ASTM D 4533	Lbs	53 X 52.5
AOS	ASTM D 4751	US Sieve	50
Flow Rate	ASTM D 4491	Gpm/ft	5
Permittivity	ASTM D 4491	Sec -1	0.05
UV Resistance	ASTM D 4355	% Strength Retained	90% @ 500 hrs

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. According to the specification requirements set forth within ASTM-6461, ASTM-D6462-3, and AASHTO M288, CFS-5027 meets or exceeds the requirements. Except when agreed upon in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling is made regarding are beyond our control. Nothing is to be construed as permission or as a recommendation to infringe our product.